

Santoprene™ 101-64

Thermoplastic Vulcanizate

Product Description	Key Features
A soft, black, versatile thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance for use in a wide range of applications. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion or blow molding. It is polyolefin based and completely recyclable.	<ul style="list-style-type: none"> UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component. Recommended for applications requiring excellent flex fatigue resistance. Excellent ozone resistance. EU Directive 2002/95/EC (RoHS) compliant.

General			
Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America South America
Applications	<ul style="list-style-type: none"> Automotive - Air Induction System Ducts Automotive - Boots and Bellows for Steering and Suspension Automotive - Plugs, Bumpers, Grommets, Clips Automotive - Seals and Gaskets Automotive - Weather Seals Consumer - Electronics Consumer - Floor Care Industrial - Seals and Gaskets Tubing 		
Uses	<ul style="list-style-type: none"> Appliance Components Automotive Applications Automotive Under the Hood 	<ul style="list-style-type: none"> Consumer Applications Diaphragms Electrical Parts 	<ul style="list-style-type: none"> Gaskets Seals Tubing
Agency Ratings	<ul style="list-style-type: none"> EU 2003/11/EC 	<ul style="list-style-type: none"> UL QMFZ2 	<ul style="list-style-type: none"> UL QMFZ8
RoHS Compliance	<ul style="list-style-type: none"> RoHS Compliant 		
Automotive Specifications	<ul style="list-style-type: none"> CHRYSLER MS-AR100 BGN DELPHI 8565 DELPHI DX300003 	<ul style="list-style-type: none"> FORD WSD-M2D379-A1 GM GMP/E/P.002 TRW TMS-P-10,365 	<ul style="list-style-type: none"> VALEO VMS-8618
Color	<ul style="list-style-type: none"> Black 		
Form(s)	<ul style="list-style-type: none"> Pellets 		
Processing Method	<ul style="list-style-type: none"> Blow Molding Coextrusion Extrusion 	<ul style="list-style-type: none"> Extrusion Blow Molding Injection Blow Molding Injection Molding 	<ul style="list-style-type: none"> Multi Injection Molding Profile Extrusion Sheet Extrusion
Revision Date	<ul style="list-style-type: none"> 11/27/2007 		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Specific Gravity	0.970	0.970	ASTM D792
Density	0.970 g/cm ³	0.970 g/cm ³	ISO 1183
Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Shore Hardness			ISO 868
Shore A, 15 sec, 73°F (23°C), 0.0787 in (2.00 mm)	69	69	
Elastomers	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100% - Across Flow (73°F (23°C))	377 psi	2.60 MPa	ASTM D412

Typical properties: these are not to be construed as specifications.

© 2010 ExxonMobil. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document, or endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they direct or indirect. ExxonMobil, the ExxonMobil Logo, the Interlocking "X" Device, and all other product names used herein are trademarks of ExxonMobil Chemical Company or its affiliates. Otherwise, all other trademarks are the property of their respective owners.

ExxonMobil Chemical Santoprene™ 101-64
Thermoplastic Vulcanizate



Rev 8-262

Elastomers	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100% - Across Flow (73°F (23°C))	377 psi	2.60 MPa	ISO 37
Tensile Strength at Break - Across Flow (73°F (23°C))	1020 psi	7.00 MPa	ASTM D412
Tensile Stress at Break - Across Flow (73°F (23°C))	1020 psi	7.00 MPa	ISO 37
Elongation at Break - Across Flow (73°F (23°C))	450 %	450 %	ASTM D412
Tensile Strain at Break - Across Flow (73°F (23°C))	450 %	450 %	ISO 37
Tear Strength - Across Flow (73°F (23°C), Die C)	131 lbf/in	23.0 kN/m	ASTM D624
Tear Strength - Across Flow (73°F (23°C), Method Bb, Angle (Nicked))	130 lbf/in	23 kN/m	ISO 34-1
Compression Set			ASTM D395B
158°F (70°C), 22.0 hr, Type 1	18 %	18 %	
257°F (125°C), 70.0 hr, Type 1	44 %	44 %	
Compression Set			ISO 815
158°F (70°C), 22.0 hr, Type A	18 %	18 %	
257°F (125°C), 70.0 hr, Type A	44 %	44 %	

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Brittleness Temperature	-76 °F	-60 °C	ASTM D746
Brittleness Temperature	-76 °F	-60 °C	ISO 812

Electrical	Typical Value (English)	Typical Value (SI)	Test Based On
Volume Resistivity			ASTM D257
73°F (23°C), 0.0800 in (2.03 mm)	1.0E+16 ohm-cm	1.0E+16 ohm-cm	
73°F (23°C), 0.130 in (3.30 mm)	5.0E+15 ohm-cm	5.0E+15 ohm-cm	
Dielectric Strength			ASTM D149
0.0800 in (2.03 mm)	730 V/mil	29 kV/mm	
73°F (23°C), 0.130 in (3.30 mm)	620 V/mil	25 kV/mm	
Dielectric Constant			ASTM D150
73°F (23°C), 0.0780 in (1.98 mm)	2.50	2.50	
Dielectric Constant			IEC 60250
73°F (23°C), 0.0780 in (1.98 mm)	2.50	2.50	

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	180 °F	82.2 °C
Drying Time	3.0 hr	3.0 hr
Suggested Max Moisture	0.080 %	0.080 %
Suggested Max Regrind	20 %	20 %
Rear Temperature	350 °F	177 °C
Middle Temperature	360 °F	182 °C
Front Temperature	360 °F	182 °C
Nozzle Temperature	370 to 430 °F	188 to 221 °C
Processing (Melt) Temp	380 to 450 °F	193 to 232 °C
Mold Temperature	50.0 to 125 °F	10.0 to 51.7 °C
Injection Rate	Fast	Fast

Typical properties: these are not to be construed as specifications.

© 2010 ExxonMobil. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document, or endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly own or control. ExxonMobil, the ExxonMobil Logo, the Interlocking "X" Device, and all other product names used herein are trademarks of ExxonMobil Chemical Company or one of its subsidiaries. Otherwise, all other marks are the property of their respective owners.

Rev 8-262

ExxonMobil Chemical Santoprene™ 101-64
Thermoplastic Vulcanizate



Run 5-262

Injection	Typical Value (English)	Typical Value (SI)
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa
Screw Speed	100 to 200 rpm	100 to 200 rpm
Clamp Tonnage	3.0 to 5.0 tons/in ²	41 to 69 MPa
Cushion	0.125 to 0.250 in	3.18 to 6.35 mm
Screw L/D Ratio	16.0:1.0 to 20.0:1.0	16.0:1.0 to 20.0:1.0
Screw Compression Ratio	2.0:1.0 to 2.5:1.0	2.0:1.0 to 2.5:1.0
Vent Depth	0.0010 in	0.025 mm

Injection Notes

Santoprene TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Injection Molding Guide.

Extrusion	Typical Value (English)	Typical Value (SI)
Drying Temperature	180 °F	82.2 °C
Drying Time	3.0 hr	3.0 hr
Melt Temperature	385 °F	196 °C
Die Temperature	390 °F	199 °C
Back Pressure	725 to 2900 psi	5.00 to 20.0 MPa

Extrusion Notes

Santoprene TPV is incompatible with acetal and PVC. For more information regarding processing and mold design, please consult our Extrusion Guide.

Aging	Typical Value (English)	Typical Value (SI)	Test Based On
Change in Tensile Strength in Air 302°F (150°C), 168 hr	-12 %	-12 %	ASTM D573
Change in Tensile Strength in Air 302°F (150°C), 168 hr	-12 %	-12 %	ISO 188
Change in Ultimate Elongation in Air 302°F (150°C), 168 hr	6.0 %	6.0 %	ASTM D573
Change in Tensile Strain at Break in Air 302°F (150°C), 168 hr	6.0 %	6.0 %	ISO 188
Change in Durometer Hardness in Air Shore A, 302°F (150°C), 168 hr	2.0	2.0	ASTM D573
Change in Shore Hardness in Air Shore A, 302°F (150°C), 168 hr	2.0	2.0	ISO 188
Continuous Upper Temperature Resistance	275 °F	135 °C	SAE J2236

Additional Information

Values are for injection molded plaques, fan-gated, 102.0 mm x 152.0 mm x 2.0 mm (4.000" x 6.000" x 0.080").
Tensile strength, elongation and tensile stress are measured across the flow direction - ISO type 1, ASTM die C.
Compression set at 25% deflection.

Legal Statement

For detailed Product Stewardship information, please contact Customer Service.

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use.

Typical properties: these are not to be construed as specifications.

© 2010 ExxonMobil. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. We do not endorse or recommend any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly own or control. ExxonMobil, the ExxonMobil Logo, the Interlocking "X" Device, and all other product names used herein are trademarks of ExxonMobil Chemical Company or one of its subsidiaries. P.W.J. 4/26/10