



Sn63 / Pb37 Leaded Solder - No Clean

4860 Series NEW

63% tin, 37% lead

M.G. Chemicals No Clean formula uses synthetically refined resin and an effective activator. Our No Clean formula wets and spreads like normal RA type flux and does not splatter.

Features / Benefits

- Meets J-STD-004 and QQ-S-571
- No Clean
- Standard Flux Core percentage at 2.2%
- Melting Point: 183 °C / 361 °F



Available Sizes

Catalog Number	Sizes Available	Diameter	Gauge	Description
4865-227G	1/2 lb (227 g)	0.032"	22	Spool
4865-454G	1 lb (454 g)	0.032"	22	Spool
4860-18G	18g (0.6 oz)	0.032"	22	Pocket pack (box of 25)