



MG PaintAbout MGlinkscontact us

homeMSDSproductsdistributorstech supportdownloads

Part Number/Keyword

print

RoHS COMPLIANT

ALL MG PRODUCTS ▾

- + Dusters & Cold Sprays
- + Cleaning Products for Electronics
- + Protective Coatings
- Adhesives
  - Cyanoacrylates
  - Electrically Conductive Adhesives
  - General Adhesives**
  - RTV Silicone Adhesives
  - Thermally Conductive Adhesives
  - Threadlockers
- + Greases and Lubricants
- + Prototyping and Circuit Repair
- + Solder and Solder Related Products
- + RTV Silicones
- + Epoxies
  - Specialty Products
- + 3D Printing

## Fast Set Epoxy

### 8332

BUY NOW

Description

Technical Data

MSDS

Applications

Resources

Uncured Properties	
Color	Clear
Cured Color	Yellowish
Mix Ratio by Volume	1:1
Part A <a href="#">Viscosity</a>	12,000 cps
Part B <a href="#">Viscosity</a>	13,000 cps
Mixed <a href="#">Viscosity</a>	12,500 cps
Part A Specific Gravity	1.16
Part B Specific Gravity	1.15
Mixed Specific Gravity	1.16
Pot Life	3 - 5 min
Mass	20 g
Tensile Strength	2,300 psi
Temperature Range	-60°F to 250°F -51°C to 121°C
<a href="#">Hardness</a> (Shore D)	80
Dielectric Constant (25°C, 100 Hz)	4.5
Specific Volume	23.7 in <sup>3</sup> /lb
Volume Resistivity	8 x 10 <sup>14</sup> ohm · cm

\*All properties given are at 25°C unless otherwise noted.

#### Related Products

[Super Cyanoacrylate Adhesive Liquid \(8333\)](#)

[Super Cyanoacrylate Adhesive Gel \(8334\)](#)

[Super Contact Cement \(8336\)](#)



© 2000 - 2014 MG Chemicals. All rights reserved.

[Site Map](#) [Terms & Conditions](#) [Contact Us](#) [Careers](#)