

LOCTITE ECCOBOND FP4322

July 2018

PRODUCT DESCRIPTION

LOCTITE ECCOBOND FP4322 provides the following product characteristics:

Technology	Epoxy
Appearance	Black
Cure	Heat cure
Application	Semiconductor, Encapsulant

LOCTITE ECCOBOND FP4322 is a high purity liquid epoxy encapsulant designed for semiconductor encapsulation. It is a high flow material which requires a cavity of flow control barrier to prevent excessive flow.

LOCTITE ECCOBOND FP4322 is suitable for encapsulating bare chips mounted to plastic substrates as well as potting of small hybrid circuit modules. Spot encapsulation of bare chips on ceramic substrates is not suggested in most cases.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):	
Spindle 7, speed 2 rpm	92,500
Spindle 7, speed 20 rpm	52,500
Specific Gravity @ 25 °C	1.69
Filler Content, %	65
Pot Life @ 25 °C (time to double viscosity), days	1
Shelf Life, days:	
@ 25°C	2
@ -40°C	120
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

Gel Time	
Gel Time @ 121 °C, minutes	11

Recommended Cure Schedule

- 2 to 3 hours @ 170°C or
- 3 to 6 hours @ 150°C

Alternate Cure Schedule

- 1 hour @ 125°C plus 4 hours @ 150°C

The recommended alternate cure schedule is designed for packages which are effected by high levels of stress.

A two-step cure will minimize stress and warpage on large substrates. Curing below 140°C is not recommended. User should gel devices immediately after dispensing to prevent moisture degradation of ultimate cure properties. Use suggested cure schedules as general guidelines; other cure schedules may yield satisfactory results.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties :

Hardness, Shore D	97
Glass Transition Temperature (Tg), °C	160
Coefficient of Thermal Expansion, in/in/°C:	
@ 40 to 120°C	30×10 ⁻⁶
Density, gm/cc	1.7
Linear Shrinkage, %	0.43
Extractable Ionic Content, ppm:	
Chloride (Cl ⁻)	25
Potassium (K ⁺)	25
Sodium (Na ⁺)	25
Moisture Absorption, 9 hour immersion @ 100°C, %	0.25

Electrical Properties:

Volume Resistivity, ohms-cm	6.2×10 ¹⁴
Surface Resistivity, ohms	1.6×10 ¹⁴
Dielectric Constant / Dissipation Factor @ 25°C:	
@ 1 KHz	3.18/0.005
@ 10 KHz	3.15/0.006
@ 100 KHz	3.04/0.11

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

DIRECTIONS FOR USE

1. Warm at room temperature until no longer cool to the touch (normally 20-60 minutes).
2. Do not thaw in an oven or water bath.
3. For best results LOCTITE ECCOBOND FP4322 should be dispensed onto a substrate warmed to approximately 90°C. This will help minimize air entrapment under bonding wire.

STORAGE

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : -40 °C .

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{psi} \times 145 = \text{N/mm}^2$

$\text{MPa} = \text{N/mm}^2$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 1

Americas
+888-9Henkel

Europe
+44.1442.233.233

Asia
+605.547.6811

For the most direct access to local sales and technical support visit: www.electronics.henkel.com

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[Loctite:](#)

[498499](#) [498501](#)